

5896A



Request a free brochure,
datasheet and drawing?
Scan the QR-code with your
mobile phone or visit
monchy.com!

Waxes	Value	Unit	Test Method
Drop Melt Point	82.2 - 87.8	°C	
Oil Content	0 - 2.5	Wt%	
Brand	Microwaxes		
Supplier	IGI		
Kinematic Viscosity	0 - 18	cSt	
Color Saybolt	-16 - 30		
Needle penetration	0 - 20	dmm	

By working closely together with our suppliers we can offer you a tailor-made solution in terms of quality, continuity and innovation. The demand for new and renewable (sustainable) raw materials is an important consideration when selecting waxes. This is one of the reasons why our portfolio is broad and tailored to your requirements.

Take advantage of our specialist knowledge

Waxes are used in a wide range of applications. Please contact us to discuss the products suitable for your application. We offer a range of waxes of different types.



De Monchy International B.V.
Rivium 1e straat 109
2909 LE Cappele aan den IJssel

Contact

+31 10 413 03 20
info@monchy.com
www.monchy.com

Visit our website to stay up-to-date about this product and the most recent version.